

AK Glass

Product Code: 7577G-HS

Product Series: Dry Glass Fabric



Technical Data Sheet

PHYSICAL PROPERTIES

Yarn	Warp direction:		136 Tex	
	Weft direction:		272 tex (Texturize)	
		<u>SI</u>	<u>US</u>	<u>Testing Standard</u>
Fabric Weight (Loom State)		730 ± 50 g/m ²	21.53 oz/yd ²	ASTM D3776
Weave Style		Double Twill		
Tensile Strength	Warp direction:	≥ 2000 N/25mm	≥ 200 kg _f /in	ASTM D5035
	Weft direction:	≥ 2000 N/25mm	≥ 200 kg _f /in	ASTM D5035
Air Permeability		40-90 cfm		

CONSTRUCTION

Density	Warp direction:	48.0 ± 2.0 /in	ASTM D3775
	Weft direction:	40.0 ± 2.0 /in	ASTM D3775
Fabric Thickness		0.90 ± 0.20 mm	ASTM D1777

DIMENSION

Roll Width		1040, 1100 mm -0,+15	ASTM D3774
Roll Length		300	ASTM D3773

Quality Assurance

AK Glass Fabric is manufactured under a Quality Management System approved by ISO 9001

Packaging

AK Glass Fabrics are wound on 7cm diameter core, wrapped in stretch film, secured by bubble wrap, and packed in standard carton box.

Listed below are the standard box dimensions for specified fabric widths. All dimensions are internal measurements.

Fabric Width 1040mm : 55cm x 118cm x 55cm

Fabric Width 1100mm : 55cm x 118cm x 55cm

Safety

Obtain, read, and understand the Material Safety Data Sheet (SDS) before use of AK Glass and AK Carbon Products

FOR FURTHER INFORMATION, PLEASE CONTACT US



ASIA KANGNAM COMPANY LIMITED

69/1 Moo 6, Tambol Thakam, Amphur Bangpakong,

Chachoengsao, 24130 Thailand

Phone: (+66) 38 573 635

Fax: (+66) 38 573 636, (+66) 38 573 734

This information and data contained herein is offered solely as a guide in the selection of a reinforcement material. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. The values listed for weight, thickness, and breaking strength are greige values, unless otherwise noted. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose.